

Vitrigraph firing schedules

Load Glass	400 Deg. Per hour to 1220 F. Hold 2 hours	300 deg per hour to 1525 Hold 3 hours	Begin pulling glass after 30 min.	Pull glass until pot is empty
------------	--	--	-----------------------------------	-------------------------------